

XOANONS® Defoamer

Model number

XOANONS®WE-D9904B

Specification

Composition	Polyether siloxane copolymer, without SiO ₂
Appearance	Transparent liquid
Solvent	— —
Active substance	100%
Density	0.99-1.03g/ml(25 ± 1)°C
Viscosity	10-50s(Tu-4 viscometer)(25 ± 0.2)°C
Flash point	>100°C

Note: This datasheet is intended to give typical results, not standard. Subject to COA.

Application system

Water-based

Properties

- No SiO₂. Good ability of deaeration. Prevent micro-bubble and pin-hole in the film of coating and ink.
- Addition with high shearing force. No recommendation for post-addition.

Incorporation

Should be added to the grind base with high shearing force to improve the compatibility between defoamer and resin. Predilution in a suitable solvent.

Suggest addition

Addition to total formulation 0.05-0.5%

Storage stability

Keep intact 24 months in original package. Products beyond the storage period may continue to be used after inspection. The container must be closed immediately after use.

package

25KG / 180KG